

Synthesis and Characterization Studies of L-Alanine Alaninium Nitrate NLO Crystal

Jayanthi Palaninathan¹, Aravind K²

¹PG and Research Department of Physics, Muthurangam Government Arts College (Autonomous), Vellore, Tamil Nadu, 632 002, India
Email: jayanthipnathan[at]gmail.com

²PG and Research Department of Physics, Muthurangam Government Arts College (Autonomous), Vellore, Tamil Nadu, 632 002, India
Department of Physics, School of Advanced Sciences, Vellore Institute of Technology, Vellore - 632014, India
Email: ak812284[at]gmail.com

Abstract: *L-alanine alaninium nitrate (LAAN), an organic nonlinear optical material was grown by slow evaporation technique at room temperature. The grown single crystal structural information was derived from X-ray Diffraction. The crystal represents the orthorhombic crystal structure. The mode of vibrations of different molecular groups present in LAAN was identified by FTIR studies. The UV-VIS-NIR spectrum reveals that the crystal has a low UV cut-off of 204.20 nm and has a good transmittance in the entire visible region. The photoluminescence spectra reveal green and blue emission at 439 nm and 468 nm respectively. The second harmonic generation efficiency was determined and is about 0.693 times that of the KDP crystal.*

Keywords: LAAN, Single crystal, PL, SHG

1. Introduction

Nonlinear optical (NLO) materials have attracted considerable attention due to their applications in laser technology, optical communications, optical switching, and optoelectronic device applications. Organic materials are suitable for nonlinear optical devices because of their high nonlinearity when compared to inorganic materials [1–6]. Recently, complexes of amino acids have been explored. Amino acids are interesting materials for NLO applications. The importance of amino acids in NLO applications is because all the amino acids have chiral symmetry and crystallize in noncentro-symmetric space groups. Many natural amino acids are individually exhibiting nonlinear optical properties because they are characterized by chiral carbons, a proton-donating carboxyl (–COOH) group, and the proton-accepting amino (–NH₂) group [1, 2, 5]. The crystal structure of L-alanine mixed with nitric acid in the ratio 1:0.5 was grown from an aqueous solution by the slow evaporation technique [1]. To characterize the above-grown crystals, studies like powder XRD, FTIR, UV–vis transmittance, PL, and SHG studies were carried out.

2. Synthesis and Crystal growth

LAAN was synthesized from L-alanine and nitric acid (HNO₃) taken in the mole ratio of 1:0.5. The calculated amounts of the reactants were thoroughly dissolved in 100ml double distilled water and stirred well for about 5 hours using a magnetic stirrer to ensure a homogeneous solution. The saturated solution was filtered using the Whatmann filter paper. The filtered solution was taken in a petri dish and covered with pinhole polythene cover to restrict the fast evaporation and it is kept in a dust-free compartment for slow evaporation under room temperature. Transparent colorless crystals were harvested in 23 days as shown in Figure 1.




Figure 1: LAAN Crystal

3. Characterization

3.1 Powder X-ray diffraction studies

The crystals have been subjected to powder X-ray diffraction studies to determine the unit cell dimensions and crystalline size. The synthesized grown crystal was scanned over the range from 10° to 90° diffraction angle as shown in Figure 2. The maximum intensity at 20.752960 (°2 Theta) angle shows the crystalline nature of the grown crystal. The average crystalline size of a grown LAAN single crystal is calculated by using the Debye Scherrer formula $D = K\lambda / \beta \cos\theta$, Where, D is the average crystalline size, K is a constant value, λ is the wavelength of X-ray (1.540 Å), β is full-width half maximum, and θ is diffraction angle. The average crystalline size of the grown crystal shows 42.73 nm [9]. From the data, it is observed that it belongs to the Orthorhombic system with unit cell parameters $a=12.303$ Å, $b=11.980$ Å, $c=5.756$ Å, $\alpha=\beta=\gamma=90^\circ$ [1-6].




Figure 2: Powder XRD pattern of LAAN

3.2 Fourier Transform Infrared (FTIR) spectral studies

The FTIR spectral analysis of L-alanine was carried out in the infrared region extending from 500 to 4000 cm^{-1} . The spectrum is shown in Figure 3. Vibrational band assignments of LAAN crystal are tabulated in Table 1. The vibrational band assignments of LAAN crystal prove the presence of expected functional groups in the compound.




Figure 3: FTIR Spectrum of LAAN

Table 1: Vibrational band assignments of LAAN crystal

S.No	Wave number (cm^{-1})	Assignments
1	2985.81	Symmetric CH_3^+ stretching
2	2935.66	CH_2 asymmetric stretching
3	2727.35	NH_2 stretching mode
4	2596.19	NH_3^+ stretching vibration
5	1614.42	NH_3^+ bending
6	1583.56	NH_3^+ bending
7	1516.05	NH_3^+ symmetric bending
8	1452.40	CH_3 symmetric bending
9	1409.96	COO^- symmetric stretching
10	1359.82	C–C stretching
11	1303.88	COO^- symmetric stretching
12	1234.44	NH_3^+ rocking
13	1149.57	C–N stretching
14	1112.93	NH_3^+ rocking
15	1012.63	CH_3 rocking
16	918.12	Torsional oscillation of NH_3^+
17	848.68	NO_3 stretching
18	771.53	NO_3 stretching
19	646.15	COO^- in plane deformation
20	538.14	Torsional oscillation of NH_3^+

3.3 UV-VIS-NIR Spectral studies

The UV–VIS–NIR spectrum gives information about the molecule through the absorption of UV and visible light. The optical transmission range, transparency cut-off, and absorbance band are the most important optical parameters. The Absorption band of LAAN is observed at 204.20 nm as shown in Figure 4. and there is no absorption band in the entire UV region [1-6]. Hence the crystal is expected to be transparent to the UV-Visible radiation in between these two wavelengths. LAAN is optically transparent in the entire UV region with a 96% transmittance level as shown in Figure 5. and a lower cut-off wavelength at 204.20 nm, is sufficient for laser radiation or other applications in the blue region [1]. LAAN crystals have a good transmission in UV as well as in visible region which is an added advantage for the crystals to be used in optoelectronic applications. The optical direct energy band gap of LAAN crystals is 5.29 eV is determined using Tauc plot energy band gap as shown in Figure 6.




Figure 4: Absorption spectra of LAAN Crystal




Figure 5: Transmittance of LAAN Crystal




Figure 6: Tauc plot energy band gap of LAAN Crystal

3.4 Photoluminescence studies

PL spectroscopy is a process in which a material absorbs electromagnetic radiation in the system of photons and re-radiates photons. The optical behavior of the title compound was analyzed by PL measurements. Figure 7. shows the emission spectra of LAAN Crystal. The emission peak with maximum intensity was obtained at 468 nm [3]. The peaks rise in UV emission. The emission peaks observed at 468 nm show blue emission. Blue emission has been obtained at 450 nm, 468 nm, 482 nm, and 492 nm. Violet emission has been obtained at 439 nm.




Figure 7: PL spectra of LAAN crystal

3.5 Second harmonic generation efficiency studies

A fundamental laser beam of 1064 nm wavelength (6 ns pulse width with 10Hz pulse rate) from an Nd-YAG laser was made to fall normally on the sample cell. The incident wavelength of the light is 1064 nm. The wavelength of the light emitted from the sample is 532 nm [1-6]. KDP crystals were powdered to an identical size and were used as reference materials in the SHG measurement. The SHG efficiency of LAAN crystal was found to be 0.693 times that of KDP crystal.

4. Conclusion

Colorless and transparent Single crystals of L-alanine alaninium nitrate (LAAN), have been grown by slow evaporation method at room temperature. Powder X-ray diffraction studies were carried out to calculate the lattice parameters of the grown crystals. From the data, it is observed that it belongs to the Orthorhombic system with unit cell parameters $a=12.303 \text{ \AA}$, $b=11.980 \text{ \AA}$, $c=5.756 \text{ \AA}$, $\alpha=\beta=\gamma=90^\circ$ and the average crystalline size of the grown crystal shows 42.73 nm. The FTIR spectrum confirmed the amino group in the compound. UV-VIS-NIR spectra reveal that the absorption band of LAAN is observed at 204.20 nm. LAAN is optically transparent in the entire UV region with a 96% transmittance level and lower cut-off wavelength at 204.20 nm. The optical energy band gap of LAAN crystals is 5.29 eV are determined. PL spectra show the emission peak with maximum intensity was obtained at 468 nm. The peaks rise in UV emission. The emission peaks observed at 468 nm show blue emission. The SHG studies show that the SHG efficiency of LAAN crystal was found to be 0.693 times that of KDP crystal. Based on these facts we propose the title compound L-alanine alaninium nitrate (LAAN) as a novel organic material for NLO applications.

References

- [1] M.L. Caroline, S. Vasudevan / Materials Letters 62 (2008) 2245–2248 ,
- [2] M.A. Ahlam, et al., Optik - Int. J. Light Electron Opt. (2013)
- [3] Aravindan, P. Srinivasan, N. Vijayan , R. Gopalakrishnan, and P. Ramasamy, Res. Technol. 42, No. 11 (2007)
- [4] Aravindan et al. / Spectrochimica Acta Part A 71 (2008) 297–304
- [5] M.L. Caroline et al. / Spectrochimica Acta Part A 79 (2011) 1936–1940
- [6] J Mater Sci: Mater Electron (2021) 32:3979–3988
- [7] K.C. Bright, T.H. Freeda / Physica B 405 (2010) 3857–3861
- [8] R. Hanumantharao, S. Kalainathan / Spectrochimica Acta Part A 86 (2012) 80–84
- [9] D. Jini, M. Aravind, L. Jothi Nirmal et al. Materials Today: Proceedings 43 (2021) 2032–2035
- [10] A.S.J. Lucia Rose et al. / Materials Chemistry and Physics 130 (2011) 950–955
- [11] R.J. Mani, et al., Optik - Int. J. Light Electron Opt. (2014),
- [12] D. Rajan Babu et al. / Journal of Crystal Growth 245 (2002) 121–125
- [13] Crystal Growth & Design, Vol. 8, No. 6, 2008 Sethuraman et al.
- [14] Crystal Growth & Design, Vol. 6, No. 11, 2006 Vijayan et al.