

First-Principles Molecular Mechanics Calculations of the Lattice Constant and Bulk Modulus for Au-Cu Nano-Alloy

M. E. Jahelnabi¹, M. H. Eisa^{1,2}, R. A. Alobaid¹, H. S. Bush¹

¹Physics Department, College of Science, Sudan University of Science Technology, Khartoum 11113, Sudan

²Department of Physics, College of Sciences, Al Imam Mohammad Ibn Saud Islamic University (IMSIU), Riyadh 11623, Saudi Arabia

Abstract: *The unique mechanical properties of nanoparticles or Nano alloys allow for novel applications in wide fields. In this paper, we calculate the mechanical properties of nanoparticles. We performed atomistic simulations to study the structure and Elastic constants for Au-Cu Nano-Alloy. We used approaches to compute the bulk modulus and lattice constant, one based on a definition in terms of the lattice parameter derivative of the total energy and another in terms of the volume derivative of the pressure often used in simulations. Both give quantitatively similar results.*

Keywords: Nano-alloy; lattice constant; bulk modulus; First principle calculation

1. Introduction

Nanoparticles or Nano-alloys are microscopic objects having at least one dimension less than 100 nm [1, 2]. When the particle size reaches the nanoscale, the crystal boundary is destroyed or the atomic density changes [2, 3]. Due to this change in physical properties, the use of nanomaterials varies considerably in many fields of science and technology [4, 5]. Gold-copper (Au-Cu) nanoparticles have been regarded as valuable tools in a variety of disciplines [6] such as the communications [7], renewable energy [8], molecular sensing [9], and medical imaging [10, 11]. Some mechanical properties of Nano alloys, such as strain, tensor, the shear constant, the hardness and the bulk modulus will aid a lot in the proper design of particles in specific applications. This paper aims at the calculation of the mechanical properties of Au-Cu nanoparticles or Nano alloys, from the calculation of the lattice constant and bulk modulus by computational method.

Computational method [12] are usually considered as very useful complementary tools to experimental studies, for instance, of the mechanical properties [13]. Therefore, in this work, we use the first-principle calculations to predict the lattice structure and bulk modulus of Au-Cu nanoparticles (hereafter referred to as Nano-alloys) with size ~ 1 nm per Nano-alloy. These calculations were performed using Quantum espresso code [14].

2. Computational Methods

The first-principles calculations carried out in this study were based on density functional theory using the Quantum Espresso package [14]. We used the generalized gradient approximation (GGA) [15] for the exchange-correlation functional. The first-principles calculations were performed under pressure-volume and lattice parameter- total energy conditions.

The first stage concerned with the optimization of the lattice constants for Au, Cu, and Au-Cu bulk materials. For this purpose we used the full-potential code called Exciting [16]. After optimizing the lattice constants we then used the optimized lattice constants with the Atomic Simulation Environment (ASE) [17] to generate the nanoparticle with 13 atoms by employing the Wulff-construction method incorporated with ASE. The generated Au nanoparticle is shown in Figure 1. Where the cubic box (dashed lines) has a lattice defined by the atomic sites for the 13 Au atoms nanoparticle placed in a corner of large empty box with a side $a \sim 10$ Å.

The structures energies were calculated using the first-principle Quantum Espresso [14], the uniform grid k-points were $(2 \times 2 \times 2)$.

The total energy calculations and lattice parameter were performed using density functional theory (DFT) as implemented in the Quantum espresso code [18].





Figure 1: (a) Au NPs, (b) Cu NPs and (c) Au-Cu NPs with 13 atoms generated with ASE Program using the Wulff-construction method

3. Results and discussion

We first present the results for structural properties. In order to obtain the equilibrium volume, we calculated the total energy for the Au NPs, Cu NPs and Gold-Copper NPs by varying hydrostatically the volume and allowing fully

relaxation of the ions. The results are shown in Figure 2. The equilibrium lattice parameter was found using the GGA functional. The calculated results for equilibrium lattice are summarized in the Table 1.






Figure 2: The calculated energy VS. Lattice parameter curves for optimizing the lattice constants as (a_{Au} , a_{Cu} and a_{Au-Cu}) NPs.

Table 1: First principles structural and bulk modulus of Au, Cu and Au-Cu NPs

Materials	a_0 (Ang)	K_0 (GPa)
Au NPs	11.32277	11.3
Cu NPS	9.80072	12.0
Au-Cu NPs	11.00800	13.5

We now turn the attention to the bulk modulus calculation. In order to obtain the equilibrium volume we calculated the pressure for the Au, Cu and Au-Cu NPs. The results are shown in Figure 3. The bulk modulus K_0 was determined from the results of total energy change with respect to the hydrostatic variation of volume and fitted to the fourth-order Birch-Murnaghan equation of state. These results in bulk modulus are summarized in the Table 1.




Figure 3: Compression data of (Au , Cu and Au-Cu) NPs at zero temperature. The solid curve is a least squares fit of the first-principles calculations data

4. Conclusion

In summary, we have presented first principles calculations of the lattice constant and bulk modulus of Au, Cu and Au-Cu NPs. Using DFT with Quantum Espresso package, one based on a definition in terms of the lattice parameter derivative of the total energy and another in terms of the volume derivative of the pressure often used in simulations. Both give quantitatively similar results.

5. Acknowledgement

The authors would like thank friends for generous support and for valuable discussions and comments. The authors supported this research privately. Furthermore, the funding which they received not lead to any conflict of interest regarding the publication of this manuscript.

References

- [1] J. Diao, K. Gall, M.L. Dunn, Atomistic simulation of the structure and elastic properties of gold nanowires, *Journal of the Mechanics and Physics of Solids* 52 (2004) 1935-1962.
- [2] D. Guo, G. Xie, J. Luo, Mechanical properties of nanoparticles: basics and applications, *Journal of Physics D: Applied Physics* 47 (2013) 013001.
- [3] Y. Pan, S. Neuss, A. Leifert, M. Fischler, F. Wen, U. Simon, G. Schmid, W. Brandau, W. Jahnen-Dechent, Size-dependent cytotoxicity of gold nanoparticles, *Small* 3 (2007) 1941-1949.
- [4] V. Mohanraj, Y. Chen, Nanoparticles-a review, *Tropical journal of pharmaceutical research* 5 (2006) 561-573.
- [5] A.S. Manmode, D.M. Sakarkar, N.M. Mahajan, Nanoparticles-tremendous therapeutic potential: a review, *International Journal of PharmTech Research* 1 (2009) 1020-1027.
- [6] A. Reverberi, N. Kuznetsov, V. Meshalkin, M. Salerno, B. Fabiano, Systematical analysis of chemical methods in metal nanoparticles synthesis, *Theoretical Foundations of Chemical Engineering* 50 (2016) 59-66.
- [7] S. Maier, M. Brongersma, P. Kik, S. Meltzer, A. Requicha, B. Koel, H. Atwater, Plasmonics—A Route to Nanoscale Optical Devices (*Advanced Materials*, 2001, 13, 1501), *Advanced Materials* 15 (2003) 562-562.
- [8] Y. Alivov, Z. Fan, Efficiency of dye sensitized solar cells based on TiO₂ nanotubes filled with nanoparticles, *Applied Physics Letters* 95 (2009) 063504.
- [9] K. Kneipp, Y. Wang, H. Kneipp, L.T. Perelman, I. Itzkan, R.R. Dasari, M.S. Feld, Single molecule detection using surface-enhanced Raman scattering (SERS), *Physical review letters* 78 (1997) 1667.
- [10] S. Lal, N.K. Grady, J. Kundu, C.S. Levin, J.B. Lassiter, N.J. Halas, Tailoring plasmonic substrates for surface enhanced spectroscopies, *Chemical Society Reviews* 37 (2008) 898-911.
- [11] C.S. Kumar, F. Mohammad, Magnetic nanomaterials for hyperthermia-based therapy and controlled drug delivery, *Advanced drug delivery reviews* 63 (2011) 789-808.
- [12] V.Y. Bodryakov, A. Bashkatov, Heat capacity of tantalum in the normal and superconducting states: Identification of the contributions, *Russian Metallurgy (Metally)* 2013 (2013) 671-675.
- [13] K. Cooper, A. Gupta, S. Beaudoin, Simulation of the adhesion of particles to surfaces, *Journal of colloid and interface science* 234 (2001) 284-292.
- [14] P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G.L. Chiarotti, M. Cococcioni, I. Dabo, QUANTUM ESPRESSO: a modular and open-source software project for quantum simulations of materials, *Journal of physics: Condensed matter* 21 (2009) 395502.
- [15] J.P. Perdew, K. Burke, M. Ernzerhof, Generalized gradient approximation made simple, *Physical review letters* 77 (1996) 3865.
- [16] A. Gulans, S. Kontur, C. Meisenbichler, D. Nabok, P. Pavone, S. Rigamonti, S. Sagmeister, U. Werner, C. Draxl, Exciting: a full-potential all-electron package implementing density-functional theory and many-body perturbation theory, *Journal of Physics: Condensed Matter* 26 (2014) 363202.
- [17] A.H. Larsen, J.J. Mortensen, J. Blomqvist, I.E. Castelli, R. Christensen, M. Dułak, J. Friis, M.N. Groves, B. Hammer, C. Hargus, The atomic simulation environment—a Python library for working with atoms, *Journal of Physics: Condensed Matter* 29 (2017) 273002.
- [18] A.D. Becke, Density-functional exchange-energy approximation with correct asymptotic behavior, *Physical review A* 38 (1988) 3098.